

FAG Rolling Bearing Grease

Arcanol MULTI2

Properties, Bearing grease for moderate and high load, low starting temperatures, wide applications: temperature range, wide speed range, improved relubricatability

Characteristics	Unit	Value	Test method
Classification:		KP2K-30	DIN 51825
Density:	[kg/dm ³]	0,95	
Specifications:			
Thickener:		lithium soap	
Type of base oil:		mineral oil	
Temperature range:	[°C]	-30 to 120	DIN 51825
Longtime limit temperature:	[°C]	75	
Base oil viscosity at 40 °C:	[mm ² /s]	≥ ISO VG 68	DIN 51562 - 1
Worked penetration:	[0,1 mm]	265-295	DIN ISO 2137
NLGI grade:		2	DIN 51518
Drop point:	[°C]	≥ 180	DIN ISO 2176
Water resistance:	[Range]	≤ 1-90	DIN 51807 - 1
Corrosion Emcor Test:	[grad]	0/0	DIN 51802
1 % NaCl:	[grad]	≤ 1/1	
Copper corrosion after 24 h/120 °C:	[Corr.Grad]	≤ 2	DIN 51811
FE8 tests run wear behaviour		Running time 500 hours, no failure	
536050 - 7,5/80/RT	[mg]	vWk50 ≤ 35 mg	DIN 51819
536050MP - 7,5/80-80	[mg]	vWk50 ≤ 35 mg	DIN 51819
FE9 tests run (grease service lifetime)			
A/1500/6000-130	[h]	F50 ≥ 100 h	DIN 51821-02
	[h]	no failure < 80 h	
Speed range:	Unit	Ball bearings and cylindrical roller bearings	Other roller bearings*)
Speed limit n*dm	[mm/min]	500.000	250.000

*) not cylindrical roller thrust bearings and spherical roller thrust bearings

This copy is not taken into account by the updating service.

The data are based on actual knowledge at the time of print and refer to the respective test method. Guaranteed properties or warranties cannot be taken over.

Edition 25.03.2009

FAG Industrial Services GmbH**Arcanol MULTI2**

Category		greases (K)
Not harmful to the environment		no
USDA-authorization		none
Available internationally		yes
Base oil type		Min (mineral oil)
Additives		oxidation inhibitors (AO) antiwear additives (AW) corrosion inhibitors (KI)
Standards / company releases		DIN 51825 - K2N-30
Thickener type		Li-soap
Kinematic viscosity (DIN 51562)	[mm²/s]	68.0 at 40°C n.d. at 100°C
NLGI consistency grade		2
Min. recommended temperature (DIN)	[°C]	-30
Min. recommended temperature (IP)	[°C]	n.d.
Max. operating temperature (DIN)	[°C]	120
According to test (DIN 51821/2)		A/1500/6000
Speed parameter	[mm/min]	500000
Dropping point	[°C]	185.0
Density	[g/cm³]	0.9
Timken OK-load		n.d.
Hazard symbols		n.d.
Free from silicone		no

All the data given were provided by the manufacturer.

The Schaeffler KG has not checked the data for either completeness or correctness.

The manufacturer should be contacted before the product is used.